




Azure 80mm

DESCRIPTION Paver TEXTURE Smooth

PALLET OVERVIEW



JOINT WIDTH: 9/32" (7 mm)
% OF SURFACE OPENING: 4.5%**
INFILTRATION RATE: 570 in./hr
 (14 475 mm/hr)


Specifications per pallet	Imperial	Metric
Cubing	ft	7.90 m ²
Approx. Weight Smooth	3 095 lbs	1 404 kg
Approx. Weight Smooth HD ²	3 280 lbs	1 488 kg
Number of rows	8	
Coverage per row	10.62 ft ²	0.99 m ²
Linear coverage per row	9.75 lin. ft	2.97 lin. m

	Unit dimensions		in	mm	Units/pallet
A	Height	3 1/8	80		32 units
	Width	13	330		
	Length	6 1/2	165		
B	Height	3 1/8	80		32 units
	Width	13	330		
	Length	13	330		
C	Height	3 1/8	80		16 units
	Width	13	330		
	Length	19 1/2	495		


PHYSICAL AND CHEMICAL PROPERTIES

SiO ₂ %	96 to 99%
Iron (Fe ₂ O ₃)%	0.56%
Alumina (Al ₂ O ₃)%	NIL
Lime (CaO)%	NIL
Magnesia (MgO)%	NIL
Loss On Ignition (LOI)%	0.38
Bulk Density (Test Method - ASTM - C97/C 97M-09):	2471.53
Bulk Specific Gravity (Test Method- ASTM C97/c 97M-09):	2.5
Water Absorption (Test Method- ASTM C97/C 97M-09):	1.6
Abrasion Resistance (Test Method- ASTM C 241/C 241M-09):	46.61
Resistance to salt Crystallization (Test method-EN12370:1999) (Mass Gain (%)):	0.68
Durability of Natural Building Stones (Test method IS 1126:1974) (Change in mass loss or Gain):	(-)0.125
Modulus of Rupture (Test Method - ASTM C99/C 99 M - 09), Average Value:	18.72
Compressive Strength, Mpa (Test Method -ASTM C170/C 170M-09):	98.82
Flexural Strength, Mpa (Test Method - ASTM C880/C 880M - 09):	16.63


01 | Modular pattern



02 | Modular pattern



03 | Linear pattern



Patterns are for design inspiration only. The installer is responsible to calculate & purchase the correct amount of material.

Terra Linea Terra Save

