


Nimbus RANDOM

DESCRIPTION: Paver TEXTURE: Multi-textured

PALLET OVERVIEW



Specifications per pallet	Imperial	Metric
Cubing	116.20 ft²	10.80 m ²
Approx. Weight	3 356 lbs	1 522 kg
Number of rows	10	
Coverage per row	11.62 ft ²	1.08 m ²
Linear coverage per row	17.71 lin. ft	5.40 lin. m



A



Unit dimensions	in	mm	Units/pallet
Height	2 ⁹ / ₁₆	65	80 units
Width	7 ⁷ / ₈	200	
Length	3 ¹⁵ / ₁₆	100	

B



Height	2 ⁹ / ₁₆	65	100 units
Width	7 ⁷ / ₈	200	
Length	7 ⁷ / ₈	200	

C



Height	2 ⁹ / ₁₆	65	90 units
Width	7 ⁷ / ₈	200	
Length	11 ¹³ / ₁₆	300	

JOINT WIDTH: 3/16" TO 9/16" (4 TO 14 mm)


% OF SURFACE OPENING: 6.3 %

INFILTRATION RATE: 610 in./hr
(15 505 mm/hr)


PHYSICAL AND CHEMICAL PROPERTIES

SiO ₂ %	96 to 99%
Iron (Fe ₂ O ₃)%	0.56%
Alumina (Al ₂ O ₃)%	NIL
Lime (CaO)%	NIL
Magnesia (MgO)%	NIL
Loss On Ignition (LOI)%	0.38
Bulk Density (Test Method - ASTM - C97/C 97M-09)	2471.53
Bulk Specific Gravity (Test Method- ASTM C97/c 97M-09):	2.5
Water Absorption (Test Method- ASTM C97/C 97M-09):	1.6
Abrasion Resistance (Test Method- ASTM C 241/C 241M-09):	46.61
Resistance to salt Crystallization (Test method-EN12370:1999) (Mass Gain %):	0.68
Durability of Natural Building Stones (Test method IS 1126:1974) (Change in mass loss or Gain):	(-)0.125
Modulus of Rupture (Test Method - ASTM C99/C 99 M - 09), Average Value:	18.72
Compressive Strength, Mpa (Test Method -ASTM C170/C 170M-09):	98.82
Flexural Strength, Mpa (Test Method - ASTM C880/C 880M - 09):	16.63


04 | Modular pattern



05 | Modular pattern



06 | Linear pattern



Patterns are for design inspiration only. The installer is responsible to calculate & purchase the correct amount of material.

Terra Linea Terra Save

