



Wavecrest

DESCRIPTION: Paver **TEXTURE:** Smooth

Specifications per pallet

Cubing Approx. Weight

Number of rows

Coverage per row

Linear coverage per row

PALLET OVERVIEW











	Length 6.	.69 lin. ft	2.0	04 lin. m
<u></u>	Unit dimensions	s in	mm	Units/pallet
₩ H	Height	t 3 15/16	100	56 units
	Width	10 ½	255	
	Length	n 20 ½	510	

Imperial

78.39 ft²

2 245 lbs

11.20 ft²

13.39 lin. ft

7

Depth

Metric

 $7.28 \; m^2$

1 018 kg

1.04 m²

4.08 lin. m

JOINT WIDTH: 1 5%" (41 mm) % OF SURFACE OPENING: 38 % INFILTRATOIN RATE: 2 395 in./hr (60 842 mm/hr)

WINTER CONDITIONS

De-icing salts should never be used on grass as salt will damage it. The snowblower blade should be set to leave a ¾ to 1 ½ in. (2 to 4 cm) tamped snow cover to protect the grass from extreme cold and prevent it from being torn off during snow removal.

5iO2%	96 to 99%
ron (Fe2O3)%	0.56%
Alumina (A1203)%	NIL
Lime (CaO)%	NIL
Magnesia (MgO)%	NIL
Loss On Ignition (LOI)%	0.38
Bulk Density (Test Method - ASTM - C97/C 97M-09);	2471.53
Bulk Specific Gravity (Test Method- ASTM C97/c 97M-09):	2.5
Water Absorption (Test Method- ASTM C97/C 97M-09):	1.6
Abrasion Resistance (Test Method- ASTM C 241/C 241M-09):	46.61
Resistance to salt Crystallization (Test method-EN12370:1999) (Mass Gain (%):	0.68
Durability of Natural Building Stones (Test method IS 1126:1974) (Change in mass loss or Gain):	(-)0.125
Modulus of Rupture (Test Method - ASTM C99/C 99 M - 09), Average Value:	18.72
Compressive Strength, Mpa (Test Method -ASTM C170/C 170M-09):	98.82
Flexural Strength, Mpa (Test Method - ASTM C880/C 880M - 09):	16.63

01 Linear pattern	02 Linear pattern	03 Herringbone pattern	04 Herringbone pattern

Patterns are for design inspiration only. The installer is responsible to calculate & purchase the correct amount of material.

Terra Save Terra Linea

